

## General Information

**Product Name:** REVAC® CBM 50

**Product Description:** REVAC® CBM is a dense, mineral loaded vinyl (MLV) sound barrier comprised of a high percentage of recycled raw materials and is specifically designed to remain flexible at lower than standard operating temperatures. The product is a cost-effective mass layer which can be used for general sound reduction applications. In addition, it has been designed to have good oil resistance properties making the product especially well suited to acoustic pipe wrap applications in the oil and gas industry. The product is free of lead, unrefined aromatic oils and bitumen. It has excellent resistance to mineral oils, greases, weak acids and alkalis.

**Construction:** Monolayer barrier

**Application:** Designed to improve the sound insulation of pipework and other structures at all frequencies. The mat is normally fixed in intimate contact with the original substrate or intermediate space layers.

## Technical Data

Description	Data	Unit	Tolerance	Test Method
Apparent Density	2100	Kg/m <sup>3</sup>	+/- 10%	DIN EN 1602
Reaction to Fire	Pass	-	-	FMVSS 302
Nominal Weight	5.0	Kg/m <sup>2</sup>	+10/- 5%	-
Nominal Thickness	2.38	mm	+20/- 10%	-
Strain at break	50	%	Minimum	ISO 37:2011 (E)
Stress at peak	1.3	N/mm <sup>2</sup>	Minimum	ISO 37:2011 (E)
Durometer hardness (Shore A)	90	-	Typical	Internal
Static Operating Temp. Range	- 40 – 95	°C	-	Internal
Colour	Black	-	-	-

## Acoustic Data

Data extrapolated from BS EN ISO 10140-2 (Free Hanging Curtain)	
Hz	Revac® CBM 50
125	13.8
250	16.4
500	21
1000	25.6
2000	31.5
4000	38
Barrier (kg/m <sup>2</sup> )	5.00
Space L	0.0
Space L	0.0
Total Mass (kg/m <sup>2</sup> )	5.00
Rw (dB) @ 1000Hz	25
Average SRI	24

